

FEMORAL HEAD SIZE IN THR: RATIONALE FOR REASSESSMENT

SUMMARY OF INVESTIGATIONS CONDUCTED IN THE ORTHOPEDIC BIOMECHANICS LABORATORY AT THE MGH

BRIAN R. BURROUGHS, MS AND WILLIAM H. HARRIS, MD
MASSACHUSETTS GENERAL HOSPITAL

INTRODUCTION

Sir John Charnley's initial endeavors in total hip replacement (THR) made use of a femoral head that was 41.5mm in diameter¹. The rationale for a component of this size was that the femoral head must be anatomically similar to the natural hip in order to restore the natural function of the hip. However, Charnley's initial attempts proved unsuccessful due to excessive wear of the mating bearing materials and subsequent component loosening. The recent advent of electron beam highly crosslinked ultra-high molecular weight polyethylenes (UHMWPE) has allowed for the reevaluation of larger femoral head sizes, as these materials have demonstrated extremely low wear *in vitro* regardless of femoral head size.

Irradiation of UHMWPE produces a host of free radicals throughout the material. If left untreated, they can persist for long periods of time and oxidize the material by reacting with oxygen diffusing in from the surrounding environment. However, if the UHMWPE is irradiated with a high-energy electron beam and melted immediately after irradiation, the free radicals react with each other to form crosslinks that provide the material with exceptional oxidation resistance. Crosslinking gives the UHMWPE a more entangled molecular structure and hence exceptional wear resistance. The dramatic improvement in wear resistance as compared to conventional UHMWPE THR bearing materials has been demonstrated *in vitro* in both pin-on-disk studies^{2,3,4,5,6,7} as well as in studies utilizing a physiological hip joint simulator^{5,8}.

There are a number of UHMWPE acetabular liners now on the market that claim to be crosslinked. However, to date, only two highly crosslinked polyethylenes (Durasul™ of Sulzer Orthopedics, Inc. and Longevity™ of Zimmer, Inc.) have demonstrated an extremely low wear rate that is independent of

femoral head size, a phenomenon not seen with conventional polyethylene bearing materials. Hip simulator testing has shown that UHMWPE irradiated with an electron beam and subsequently melted provides exceptionally low wear for femoral head sizes up to 46 mm⁵. Considering this behavior, it is reasonable to revisit the use of a larger femoral head in THR.

Conceptually, the advantages of larger femoral heads are increased range of motion and joint stability. There is some debate in the literature on whether THR dislocation is a significant problem, although one must consider that the cause of dislocation is multifactorial⁹ and that recurrent dislocation is a cause for early revision^{10,11}. Even though dislocation rates for primary THR are typically reported to be low, some studies have reported rates as high as 5.8%^{12,13}. Dislocation rates for revisions have been reported to range from 4.8% to 13%^{13,14,15}. 30%^{13,16} to 65%^{17,18} of THR dislocations become recurrent. An inverse relationship has been shown between the number of THRs performed by a surgeon and the rate of dislocation^{19,20,21}. Other factors that affect the potential for dislocation include preoperative diagnosis, surgical approach, postoperative management, component position, and component design.

Considering that impingement can be a precursor to dislocation, total hip designs which provide increased range of motion before impingement may be more stable. Several studies have shown that increasing the head/neck ratio results in an increase in range of motion^{22,23,24}. One means of increasing the head/neck ratio is to increase the diameter of the femoral head.

Larger femoral heads can also increase joint stability by increasing the displacement between the femoral head and acetabulum required for dislocation. This greater displacement produces greater tension on the soft tissues surrounding the hip during subluxation, resulting in a greater reaction force that acts to keep the head within the socket.

MATERIALS AND METHODS

RANGE OF MOTION TESTING

Range of motion tests were conducted on a three dimensional anatomic goniometer²⁴, which consists of a Sawbone® pelvis and femur into which total hip components are implanted. A 61 mm OD acetabular shell (Interop®, Sulzer Orthopedics, Austin, TX) was placed in the left acetabulum of the Sawbones® pelvis (Pacific Research Laboratories, Vashon, WA). The acetabular shell was positioned in 45° of abduction and 30° degrees of anteversion.

Brian R. Burroughs, MS is Research Project Manager, Orthopaedic Biomechanics and Biomaterials Laboratory.

William H. Harris, MD, DSc is an Alan Gerry Clinical Professor of Orthopaedic Surgery, Harvard Medical School.

Address correspondence to:

William H. Harris, MD
Orthopaedic Biomechanics and Biomaterials Laboratory
Gray/Jackson 1126
Massachusetts General Hospital
55 Fruit Street
Boston, MA 02114
Email: wharris.obbl@partners.org

Two femoral components with different neck geometries were used in the Sawbones® femur: the Natural® stem (Sulzer Orthopaedics, Austin, TX.) which has a straight cylindrical neck with a less prominent collar, and the cemented Versys® stem (Zimmer, Inc., Warsaw, IN), which has a tapered trapezoidal neck with a more prominent collar. These two neck designs are believed to be representative of many currently available neck geometries. Both stem types in this study used a 12/14 morse taper and therefore allowed for the testing of all femoral head diameters and lengths on both stems types. Each femoral component was inserted in neutral varus/valgus angulation, with varying degrees of femoral anteversion (0, 15, and 30 degrees).

This setup was used to test the range of motion in pure flexion, internal rotation at 90° of flexion, and external rotation at 0° of extension. The femoral head sizes tested were 28 mm, 32 mm, 38 mm, and 44 mm in diameter. The 28 and 32 mm heads (Zimmer, Inc. Warsaw, IN) were tested in five head-neck lengths; -3.5, 0, +3.5, +7 (skirted), and +10.5 (skirted) mm. The 38 mm and 44 mm heads (Sulzer Orthopaedics, Austin, TX) were tested in -8, -4, 0, +4, and +8 mm neck lengths, none of which were skirted. For each case, the amount of motion as well as the type of impingement (i.e. component-on-component, component-on-bone, bone-on-bone) was recorded.

DISLOCATION TESTING

To evaluate joint stability, a novel device was constructed to enable replication of hip flexion to the point of dislocation. The device consists of a Sawbones® hemipelvis, a fiberglass femur (Pacific Research Laboratories, Vashon, WA), and a cradle that supports the pelvis. Flexion of the hip was produced by rotating the cradle about an axis aligned with the center of the femoral head. A precision voltage potentiometer was mounted on the shaft about which the cradle (i.e. pelvis) rotated, which allowed for the continuous measurement of flexion angle via a computer data acquisition system (Omega Engineering, Inc., Stamford, CT). The entire device was mounted into a mechanical testing machine (MTS, Eden Prairie, MN) and load provided by the MTS combined with the load of a dead weight produced a joint reaction force in the anterior-medial direction in accordance with data from Kotzar *et al.*²⁵ The load was also continuously measured by the computer data acquisition system.

One set of dislocation tests was conducted with the femoral component (Natural®, Sulzer Orthopaedic, Austin, TX) fixed at 15° of anteversion but with the 61mm OD acetabular component in three different positions (10°, 30°, and 45°) of acetabular anteversion. In this test, the 28 mm, 32 mm, 38 mm, and 44 mm femoral heads were evaluated at neutral neck lengths in the dislocation simulator. Because the larger femoral heads do not require any countersinking within the polyethylene, the acetabular component made for the 38mm and 44mm heads had a very shallow (nearly zero) chamfer. Each test was conducted three times and Student's t-test was performed to evaluate the significance of the resulting translation and flexion required for dislocation.

RESULTS AND DISCUSSION

Note: A complete manuscript containing all data and figures has been submitted to and is under review for the Journal of Bone and Joint Surgery.

Range of motion testing showed that an increase in head size resulted in an increase in range of motion in all directions tested, up to the 38mm femoral head size. For reasons discussed below, the 44mm head did not provide any additional range of motion as compared to the 38mm head. The increase in range of motion when going from smaller head sizes (i.e. 28mm and 32mm) to a 38mm head was several degrees (2°-4°). However, at longer neck lengths where the smaller heads require a skirt, the improvement in range of motion with the larger heads was more dramatic (10+ degrees). The fact that larger femoral heads do not require a skirt to achieve longer neck lengths is of great benefit, as a skirted neck reduces the head/neck ratio and therefore limits range of motion, increasing the risk of dislocation.

When observing the type of impingement, larger heads exhibited virtually no component-to-component impingement, which was fairly prevalent with smaller head sizes. The absence of component-to-component impingement with the larger heads was due to the absence of the skirt at longer neck lengths as well as the greater range of motion achieved with the greater head/neck ratio. In the case of the large head, bone-to-bone impingement occurs prior to component-to-component impingement. As a result, once bone-to bone contact occurs, no further improvement in range of motion will be achieved by further increasing the femoral head size. Thus, there was no difference in range of motion between the 38mm and 44mm head. These trends in ranges of motion and types of impingement were observed for both femoral neck designs tested.

Increasing femoral anteversion resulted in greater amounts of pure flexion and internal rotation at 90° of flexion for all head sizes tested. However, increasing femoral anteversion also produces a decrease in the amount of external rotation at 0° of extension. The anatomic goniometer testing showed that 30° of femoral anteversion combined with a 38mm femoral head still allowed for 45° to 50° of external rotation with the hip in extension.

In our dislocation simulations, we found that increasing head size resulted in greater flexion as well as greater displacement between the femoral head and acetabulum to produce dislocation. For the different acetabular anteversions tested, only the 38mm and 44mm femoral heads produced a significant increase in flexion and displacement required to produce dislocation.

The *in vitro* analysis summarized here supports the conceptual advantages of larger femoral head sizes in THR. There is also clinical support for the use of larger femoral head sizes for increasing joint stability. *In vivo* experience with bipolar reconstructions²⁶, femoral head surface replacements²⁷, and larger head diameters used with conventional polyethylene²⁸ in cases of recurrent dislocation strongly sup-

ports the findings of this *in vitro* study. The use of large femoral heads, now made possible by the advent of highly crosslinked

UHMWPE, offers promise in improving the functionality and stability of THR.

References

1. Charnley J. Surgery of the hip-joint. Present and future developments. *British Medical Journal*, 1960.
2. Bragdon CR, O'Connor DO, Lowenstein JD, et al. A New Pin-on-Disk Wear Testing Method for Simulating Wear of Polyethylene on Cobalt-Chrome Alloy in Total Hip Arthroplasty. *J Arthroplasty* 2001;16:658-665.
3. Edidin AA, Pruitt L, Jewett CW, et al. Plasticity-induced damage layer is a precursor to wear in radiation-cross-linked UHMWPE acetabular components for total hip replacement. *J Arthroplasty* 1999;14:616-627.
4. McKellop H, Shen F-W, Lu B, et al. Development of an extremely wear resistant ultra-high molecular weight polyethylene for total hip replacements. *J Orthop Res* 1999;17:157-167.
5. Muratoglu OK, Bragdon CR, O'Connor DO, et al. A novel method of crosslinking UHMWPE to improve wear, reduce oxidation and retain mechanical properties. *J Arthroplasty* 2001;16:149-160.
6. Saikko V, Ahlroos T. Wear simulation of UHMWPE for total hip replacement with a multidirectional motion pin-on-disk device: effects of counterface material, contact area, and lubricant. *J Biomed Mater Res* 2000;49:147-154.
7. Saikko V, Calonius O, Keranen J. Effect of counterface roughness on the wear of conventional and crosslinked ultrahigh molecular weight polyethylene studied with a multi-directional motion pin-on-pin device. *J Biomed Mater Res* 2001;57:504-512.
8. Muratoglu OK, O'Connor DO, Bragdon CR, et al. A new concept of larger diameter femoral heads used in conjunction with a highly crosslinked UHMWPE. *J Arthroplasty* 2001; S16: 24-30.
9. Berry DJ. Unstable total hip arthroplasty: Detailed Overview. *AAOS InstructCourse Lect* 2001;50: 265-274.
10. Etienne A, Copic Z, Charnley J. Postoperative dislocation after Charnley low-friction arthroplasty. *Clin Orthop* 1978;132:19-23.
11. Woo RYG, Morrey BF. Dislocations after total hip arthroplasty. *J Bone Joint Surg* 1982;64-A:1295-1306.
12. Flackler CD, Poss R. Dislocation in total hip arthroplasties. *Clin Orthop* 1980;151:169-178.
13. Turner RS. Postoperative total hip prosthetic femoral head dislocations: incidence, etiologic factors, and management. *Clin Orthop* 1994;301:196-204.
14. Daly PJ, Morrey BF. Operative correction of an unstable total hip arthroplasty. *J Bone Joint Surg*. 1992;74-A: 1334-1343.
15. Li E, Meding JB, Ritter MA, et al. The natural history of a posteriorly dislocated total hip replacement. *J Arthroplasty* 1999;14:964-968.
16. Hedlundh U, Ahnfelt L, Hybbinette CH, et al. Dislocations and the femoral head size in primary total hip arthroplasty. *Clin Orthop* 1996;333: 226-233.
17. Hedlundh U, Ahnfelt L, Hybbinette CH, et al. Surgical experience related to dislocations after total hip arthroplasty. *J Bone Joint Surg* 1996;78-B: 206-209.
18. Katz J, Losina J, Barrett J, et al. Association between hospital and surgeon procedure volume and outcomes of total hip replacement in the US Medicare population. Accepted for publication in *J Bone Joint Surg Am*.
19. Kreder HJ, Deyo RA, Koepsell T, et al. Relationship between the volume of total hip replacements performed by providers and the rates of postoperative complications in the state of Washington. *J Bone Joint Surg* 1997;79-A:485-494.
20. Dorr LD, Wan Z. Causes of and treatment protocol for instability of total hip replacement. *Clin Orthop* 1998;355:144-151.
21. Dorr LD, Wolf AW, Chandler R, et al. Classification and treatment of dislocations of total hip arthroplasty. *Clin Orthop* 1983;173:151-158.
22. Amstutz HC, Ludwig RM, Schurman DJ, et al. Range of motion studies for total hip replacements: a comparative study with a new experimental apparatus. *Clin Orthop* 1975;111:124-130.
23. Chandler DR, Glousman R, Hull D, et al. Prosthetic hip range of motion and impingement: the effects of head and neck geometry. *Clin Orthop* 1982;166:284-291.
24. Krushell RJ, Burke DW, Harris WH. Range of motion in contemporary total hip arthroplasty: the impact of modular head-neck components. *J Arthroplasty* 1991; 6:97-101.
25. Kotzar GM, Davy DT, Goldberg VM, et al. Telemeterized *in vivo* hip joint force data: a report on two patients after total hip surgery. *J Orthop Res* 1991;9:621-633.
26. Parvizi J, Morrey BF. Bipolar hip arthroplasty as a salvage treatment for instability of the hip. *J Bone Joint Surg* 2000;82-A:1132-1139.
27. Amstutz HC, Graff-Radford A, Mai LL, et al. Surface replacement of the hip with the Tharies system. Two to five-year results. *J Bone Joint Surg* 1981;63-A:1069-1077.
28. Amstutz HC, Udombiat P, Beaulé PE, et al. A large diameter femoral ball for the prevention and treatment of dislocation after total hip replacement. 12th Annual International Symposium for Technology in Arthroplasty, Chicago, IL, Sept. 23rd-25th, 1999.